

ABSOLUTE FORCE

MACHINE FILM

Property	ASTM Method	Value
Thickness (Mil)		0.57
Haze	D-1003	1.5
Tensile Properties		
Elongation % (MD)	D-882	585%
Elongation % (TD)	D-882	705%
Tensile Ultimate (MD)	D-882	5900 PSI
Tensile Ultimate (TD)	D-882	4570 PSI
Elmendorf Tear (gram/sheet)	D-1922 (MD)	240
Elmendorf Tear (gram/sheet)	D-1922 (TD)	305
Dart Drop (gram/sheet)	D-1709	320